

## MATERIAL DATA SHEET

Parameter	Value	Unit	Standard
Basic weight	165 <sup>(+/-)5</sup>	g/m <sup>2</sup>	PN-ISO 536
Thickness	169 <sup>(+/-)6</sup>	µm	PN-ISO 534

**Adhesive:** Synthetic rubber-based pressure sensitive hot-melt. Good balance of tack, good peel and shear properties, no staining on face stock paper.

Peel adhesion (FTM1)	18	N/25 mm	-
Loop tack (FTM9)	36	N/25 mm	-
Min. application temperature	5	°C	-
Service temperature	(-25)+60	°C	-

**Face stock:** matt coated inkjet paper – printable with all dye- and pigmented inks.

Basis weight	85 <sup>(+/-)4</sup>	g/m <sup>2</sup>	PN-ISO 536
Thickness	107 <sup>(+/-)5</sup>	µm	PN-ISO 534
CIE Whiteness	150 <sup>(+/-)6</sup>	-	PN-ISO11475

**Liner:** adhesive glassine paper

Basis weight	60 <sup>(+/-)3</sup>	g/m <sup>2</sup>	PN-ISO 536
Thickness	53 <sup>(+/-)4</sup>	µm	PN-ISO 534
Release	0,18 <sup>(+/-)0,06</sup>	N/25 mm	Finat-10 (Tesa tape 4651)

Storage conditions: constant temperature (18-25°C) and humidity (40-55%). Warehouse should be clean and dry. Materials, if not used, should stay in their original packaging, or be well protected against dust and dirt. Do not expose to direct sunlight and any other heat sources.

Shelf life: 24 months, c

*This product data sheet is intended to be as used as a guideline only. All products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. The manufacturer reserves the right to change these parameters at any time without prior notice.*

04.07.2019